
ZIITEK ELECTRONIC MATERIAL & TECHNOLOGY CO.,LTD



TIF[™]100N-40-10F Thermally Conductive Gap Filler Pads Series

REV03



Features

- Sood thermal conductivity
- » Naturally tacky needing no further adhesive coating
- Soft and Compressible for low stress applications
- » Available in varies thickness


Application

- Cooling components to the chassis of frame
- Set Top Box
- » Car Battery & Power Supply
- » Charging Pile
- » LED TV/ Lighting
- » Graphics Card Thermal Module


TIFTM100N-40-10F Series thermally conductive interface materials are applied to fill the air gaps between the heating elements and the heat dissipation fins or the metal base. Their flexibility and elasticity make them suited to coat very uneven surfaces. Heat can transmit to the metal housing or dissipation plate from the heating elements or even the entire PCB, which effecitly enhances the efficiency and life-time of the heat-generating electronic components.

Typical Properties of TIF [™] 100N-40-10F Series		
Property	Value	Test method
Color	Gray	Visual
Construction	Ceramic filled silicone elastomer	*****
Thickness range	0.020"(0.5mm)~0.200" (5.0mm)	ASTM D374
Hardness (Shore 00)	55±5	ASTM 2240
Density (g/cm³)	2.1	ASTM D792
Operating Temp	-40~160℃	*****
Dielectric Constant@1MHz	4.7	ASTM D150
Thermal Conductivity (W/mK)	4.0	ASTM D5470
	4.0	ISO22007-2
Flame Rating	94 -V0	UL E331100

Pressurevs.Thermal Resistance



Pressure vs. Compression Ratio



Product Specification

Product Thicknesses: 0.020-inch to 0.200-inch (0.5mm to 5.0mm) **Product Sizes:** 8" x 16"(203mm x406mm)
Individual die cut shapesand and custom thickness can be supplied. Please contact us for confirming
Safe disposal method does not require special protection. The storage condition is low temperature and dry, away from open fire and away from direct sunlight. For detailed method, please refer to the product material safety data sheet.

Thermally Conductive Materials Thermally Conductive Plastics Heat Generating Materials Shielding Materials Foaming Silica Gel

Canada:

Tel:+001-604-2998559 E-mail: frances@thermazig.com China: Tel: +86-769-38801208 E-mail: frances@ziitek.com.tw

Taiwan:
Tel:+886-2-22771007
E-mail:frances@ziitek.com.tw

2/28/2020